



BOREAL Taupe 95

This plain fabric is available in a range of 20 colours, suitable for any style and mood.

Technical properties



Flame retardant



Acoustic

Applications Valences - Lining - Bed runners - Curtains - Roman blinds

Composition 100% FR polyester

Weight 260 g/m²

Width 290 cm

Fabric direction Room high or standard direction

Fitting ↔ cm ↓ cm

Maintenance advice     

Label OekoTex

Minimum order 1 linear(s) meter(s)



Technical characteristics

| | | |
|-----------------|-----------------------------------------------------------|------------------------|
| Flame retardant | M1 / IMO PASS | |
| Acoustic | Noise reduction coefficient (NRC) : | 0.88 |
| | Weighted sound absorption coefficient (a _w) : | 0.90 |
| | Acoustic absorption class (a _w) : | A |
| Optical index | Light reflexion : | 3 % |
| | Light absorption : | 97 % |
| | Light transmission : | 0 % |
| Thermal index | Solar reflexion : | 30 % |
| | Solar absorption : | 69 % |
| | Solar transmission : | 1 % |
| | UV transmission : | 0 % |
| | Gtot : | Gt 51 % Fc 73 % |
| | | |
| Resilience | Lightfastness (units Class/8) | 6 |
| | Dimensional Stability (%) | |
| | Warp | -1 |
| | Weft | -2 |
| | Martindale (Cycles) | 0 |
| | Breaking Elongation | |
| | Warp | 28 |
| | Weft | 24 |
| | Breaking load (daN) | |
| | Warp | 120 |
| Weft | 78 | |

